



# POLY MAX® HIGH TACK EXPRESS

UNIVERSAL CONSTRUCTION ADHESIVE AND SEALANT WITH HIGH INITIAL GRIP AND FAST FINAL STRENGTH BUILD-UP.



## PRODUCT DESCRIPTION

Universal assembly adhesive and sealant based on unique SMP technology, with high initial bond strength and fast final strength build-up. For bonding, fixing and sealing almost all (construction) materials on almost all surfaces (both smooth, porous and non-porous surfaces). Very high initial grip. Super fast. Permanently elastic.

## FIELD OF APPLICATION



Bonding: e.g. glass, stone, natural stone, concrete, plasterwork, many synthetic materials, wood, chipboard, Trespa®, iron, aluminium, zinc, steel, stainless steel and other metals, ceramic tiles, cork and mirrors. Fixing: e.g. skirting boards, lathing, window sills, doorsteps, roof edges, construction boards, insulation materials, gypsum boards, polystyrene ornaments and decorative frames. Sealing: e.g. skirting boards (synthetics), window frames, stair steps, window sills, doorsteps and drywalls. Also suitable for sealing cracks in walls and ceilings. Not suitable for PE, PP, PTFE and bitumen. When gluing plastics always perform an adhesion test first. Adhesion to plastics can vary depending on the type of synthetic and the quality of the plastic.

## PROPERTIES

- Very high initial bond strength
- Super-fast building of final bonding strength
- Very high final bond strength
- Permanently elastic
- Can be used internally and externally
- Paintable (test first)
- Good filling capacity
- Resistant to temperatures between -40°C and +100°C

- UV, water and all-weatherresistant
- 100% adhesive (non-shrinking)
- Also bonds to slightly damp surfaces
- Solvent-free
- Excellent bonding without primer
- Acid-free, odourless

## CERTIFICATES & STANDARDS

Certificates	
	TÜV: Approved and certified by TÜV Rheinland on shear strength, tensile strength, elasticity and adhesion to different materials. Certificate TÜV 43168.
	EMICODE: Classification system (GEV) of emission properties for construction products in indoor areas. EC-1 Plus (Very low emission Plus)

## PREPARATION

**Working Conditions:** Only apply at temperatures between +5°C and +40°C.

**Surface Requirements:** Both parts must be solid, clean, free of dust and grease. Use of primer not required. The surface may be slightly moist.

**Tools:** Use putty knife or spatula to apply. If necessary, use a rubber mallet to tap lightly. For surface bonding use a glue spreader (2 mm).

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.



# POLY MAX® HIGH TACK EXPRESS

UNIVERSAL CONSTRUCTION ADHESIVE AND SEALANT WITH HIGH INITIAL GRIP AND FAST FINAL STRENGTH BUILD-UP.

## APPLICATION

**Coverage:** With spot bonding: 5-8 m<sup>2</sup>/kg.

### Directions for use:

Before using, pierce the tube membrane with the puncture point integrated into the cap.

Bonding and fixing: Apply in stripes or dots (every 10 - 40 cm). Always apply to the corners and along the edges of construction boards. Correctly position material within 10 minutes and press firmly or lightly tap with a rubber mallet. If necessary, clamp or fixate heavy materials for 4 hours. Can be handled after 30 minutes (the connection is now strong enough to withstand transportation or a light load), maximum final strength after approx. 4 hours, depending on the surface and the ambient conditions. Sealing: Evenly apply to the bottom of the joint and tool within 10 minutes using a moistened (with soapy water without lemon) putty knife, sealant smoother, or finger. Tool the vertical joints from bottom to top. Fully cured after a few days (depending on the thickness of the layer). When painting over with alkyd paint, the paint may dry more slowly.

**Stains/residue:** Use white spirit for cleaning tools and removing wet adhesive residue. Dry adhesive residue can only be removed mechanically.

**Points of attention:** The following drying times are based on bonding at least one porous material and an adhesive layer of approx. 1 mm thickness. If two non-porous materials are being bonded and/or the layer of adhesive is thicker, the drying times may be substantially longer.

## TECHNICAL SPECIFICATIONS

100% modulus:	1.7 MPa
Bonding technique:	1-Sided application
Chemical base:	SMP Polymer
Chemicals resistance:	Good
Cure rate:	1.5 mm/24h
Density approx.:	1.43 g/cm <sup>3</sup>
Elasticity:	Good
Elongation of rupture:	200 %
Filling capacity:	Very good
Final bond strength after:	4 hours. This might vary, based on circumstances, like materials, temperature and humidity.
Hardness (Shore A):	60
Initial Bonding after:	30 minutes. This might vary, based on circumstances, like materials, temperature and humidity.
Minimum temperature resistance:	-40 °C
Maximum temperature resistance:	100 °C
Mildew resistance:	Good
Moisture resistance:	Very good
Paintability:	Good
Shear strength:	350 N/cm <sup>2</sup>
Skinover time:	10-15 minutes
Solid matter approx.:	100 %
Solvent free:	Yes
Tensile strength (N/cm <sup>2</sup> ) approx.:	250 N/cm <sup>2</sup>
UV resistance:	Good
Viscosity:	Pasty
Water resistance:	Good

## STORAGE CONDITIONS

Close container properly and store in a dry, cool and frost-free place.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.